



REVISIONS			
REV	DESCRIPTION	DATE	BY



P/N	As supplied: inside diameter (min.)	After recovery: inside diameter (max.)	After recovery: wall thickness (min.)	Reel / Meter
14373RA13	1,2	0,6	0,33	150
14374RA13	1,6	0,8	0,36	150
14375RA13	2,4	1,2	0,42	150
14376RA13	3,2	1,6	0,42	150
14377RA13	4,8	2,4	0,52	75
14378RA13	6,4	3,2	0,54	75
14379RA13	9,5	4,8	0,54	50
14380RA13	12,7	6,4	0,62	50
14381RA13	15,9	7,9	0,67	30
14382RA13	19,1	9,5	0,75	30
14383RA13	25,4	12,7	0,85	30
14384RA13	31,8	15,9	0,85	30
14385RA13	38,1	19,1	0,96	30
14386RA13	50,8	25,4	1,96	30
14387RA13	76,2	38,1	1,2	15

Notes:

Heat shrink tubing type: H-1
Shrink ratio: 2:1
UV resistant
Operating temperature: -55 °C +105 °C
Minimum shrink temperature: +70°C
Minimum full recovery temperature: + 95°C
Halogen free
Longitudinal change 0 ± 10% max.

				TITLE HEAT SHRINK TUBING 2:1	
				MATERIAL CROSSLINKED POLYOLEFIN	DATE 24/05/2022
					DRAWN A.C.
PART NUMBER SEE TABLE		DRAWING NUMBER 22.05.24.14XXX.0.E		COLOR TRANSPARENT	CHECK
SIZE A4	SCALE NTS	UNIT mm.	REV A	UNLESS OTHERWISE SPECIFIED TOLERANCE SEE ABOVE	APPROVED